

PRODUCT SPECIFICATIONS

## Isoflex EIA 30 Mil Non-Reinforced

PROPERTY	TEST	UNIT	Isoflex EIA - Reinforced
Thickness	ASTM D751	mils (mm)	30.0 (±5%) (0.76)
Weight	ASTM D751	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	27 (915)
Tearing Resistance (Grave Tear)	ASTM D1004	pli (N/25mm)	9 (39)
Breaking Strength (1" Strip Tensile)	ASTM D751-B	lbs (N)	50 (222)
Elongation (1" Tensile)	ASTM D751-B	%	200.0
Adhesion – Wedge Weld	ASTM D413	lb/2in (N/50mm)	15 (66)
Dimensional Stability (max)	ASTM D1204	%	3.0
Low Temperature Bend Test	ASTM D2136	°F (°C)	-30 (-34)

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.