

PRODUCT SPECIFICATIONS

Nilex Nonwoven 4506E

PROPERTY	TEST	UNIT	VALUE (MARV)
Physical Properties			
Mass/Unit Area	ASTM D-5261	g/m ² (oz/yd ²)	203 (6.0)
Thickness	ASTM D-5199	mm (mils)	2.0 (80)
Mechanical			
Grab Tensile Strength	ASTM D-4632	N (lb)	756 (170)
Elongation	ASTM D-4632	%	50
CBR Puncture*	ASTM D-4833	N (lb)	1935 (435)
Trapezoidal Tear	ASTM D-4533	N (lb)	311 (70)
Hydraulic			
Apparent Opening Size	ASTM D-4751	mm (US Sieve)	0.212 (#70)
Permittivity	ASTM D-4491	sec ⁻¹	1.5
Permeability	ASTM D-4491	cm/sec	0.38
Water Flow Rate	ASTM D-4491	l/m/m ² (gpm/ft ²)	4482 (110)
Endurance			
UV Resistance	ASTM D-4355	% retained at 500 hrs	70
Packaging			
Roll Size	Measured	m (ft)	4.57 x 91.5 (15 x 300)

*Note: Mullen Burst ASTM D-3786 and Puncture Strength ASTM D-4833 are no longer recognized by ASTM Committee D35 as an acceptable geotextile test method. Puncture Strength ASTM 4833 has been replaced with the Static (CBR) Puncture ASTM D-6241. For more information, refer to the ASTM website at www.astm.org

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.